

Material Data Sheet F111-B85

FPM-black F111 (bisphenol cross linked)

General

F111-B85 is a black Fluorocarbon elastomer, commonly referred to as VITON* and FPM. FPM materials have a very high resistance to hydraulic fluids, chemicals and a number of organic compounds and operate in temperatures between -25 to +210°C. F111-B85 is recommended for applications where its outstanding resistance to heat, chemicals, weathering and ozone is required.

Physical properties

Density:	DIN 53479	g/cm ³	1,878
Hardness at 20°:	DIN 53505	Shore A	85
Tensile strength:	DIN 53504	N/mm ²	> 11,5
Elongation at break:	DIN 53504	%	> 180
100% Module:	DIN 53504	N/mm ²	7,4
Tear strength:	DIN 53507B	N/mm	6,4
Compression set: 24h/175°	DIN 53517	%	32,8
Min. service temperature:		°C	-25
Max. service temperature:		°C	210
Short time max. service temp. in air:		°C	280

Chemical resistance

Water up to 90°	S	Biodegradable oils	R
Steam	U	Hydrocarbons	R
HFA, HFB, HFC Fluids	S	Alcohols	U
HFD-S, R	R	Diesel, Gasoline, Fuels	R
Mineral oils	R	Ozone, Oxygen	R
Vegetable oils	R	Air up to 200°	R
Silicone oils	R		

Key to chemical resistance: **R = resistant** **S = suitable** **U = unsuitable**

Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energizers (preload elements). Applications where high temperature and/or chemical resistance is required.

Analysis and Evaluation

The mentioned properties are only valid for test pieces of the corresponding ISO, DIN and ASTM standards. They cannot be directly related to seals, gaskets and other sealing products and should be used only as a general guide.

*) VITON is a reg. Trademark of Du Pont Co./U.S.A.