

Material Data Sheet Guide Tape TB

PTFE-BR40 T110 - brown

General

T110-BR40 is a PTFE (Polytetrafluorethylene) filled with 40% bronze in brown color. The fillers make the material more resistant to “cold flow” and provide the necessary properties to use it as composite seals with energizer to withstand high pressures. It has similar chemical resistance and can be used in the same temperature range like virgin PTFE what makes it a very universal seal material. T110-BR40 should not be used for dynamic applications in water.

Physical properties

Density:	DIN 53479	g/cm ³	3,05 – 3,12
Hardness:	ASTM D2240	Shore D	62 - 67
Tensile strength:	ASTM D4894	N/mm ²	23 - 28
Elongation at break:	ASTM D4894	%	200 - 250
Coefficient of friction (dyn.):	ASTM D1894	μ	0,13
Wear factor (K):	ASTM D3702	³ min 10 ⁻⁸ /kg r	9 - 13
Compr. strength at 1% deformation:	ASTM D695	N/mm ²	7 - 9
Min. service temperature:		°C	- 200
Max. service temperature:		°C	260
Therm. Exp. Coeff. (lin.) 25-100°:	ASTM D696	10-5/°C	10 – 11,5

Chemical resistance

Water up to 70°	R	Vegetable oils	R
Water up to 90°	R	Fuels	R
HFA	R	Ozone	R
HFB	R		
HFC	R	Air up to 100°	R
HFD	R	Air up to 150°	R
Mineral oils	R	Air up to 200°	R

Key to chemical resistance: **R = resistant** **S = suitable** **U = unsuitable**

Main application

Piston / Rod seals with spring or elastomere energizer, rotary seals, back-up rings, special seals and O-rings, high and low temperature applications, chemical resistance required, low friction applications.

Analysis and Evaluation

The properties relate to fundamental values of PTFE. Product values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory.