

## Material Data Sheet HN112-B85

### H-NBR HN112 – black (peroxide cross linked)

#### General

HN112-B85 is a black hydrogenated acrylonitrile-butadiene-rubber commonly referred to as H-NBR. Good physical characteristics and chemical resistance to the most common hydraulic fluids makes it an excellent sealing material. H-NBR materials are often used in vegetable and animal oils as well as in high addivated oils, sour oils/gases (H<sub>2</sub>S) and crude oils.

#### Physical properties

Density:	DIN 53479	g/cm <sup>3</sup>	1,23
Hardness at 20°:	DIN 53505	Shore A	85
Tensile strength:	DIN 53504	N/mm <sup>2</sup>	> 18
Elongation at break:	DIN 53504	%	> 200
Compression set: 22h/100°	DIN 53517A	%	20
Compression set: 22h/150°C	DIN 53517A	%	22
Min. service temperature:		°C	-25
Max. service temperature:		°C	150

#### Chemical resistance

Water up to 90°	R	Diesel Fuel	R
Steam	U	Gasoline Fuel	S
HFA, HFB, HFC Fluids	R	Ozone	R
Mineral oils	R	Alcohols	R
Vegetable oils	R	Air up to 80°	R
Silicone oils	S		
Biodegradable oils	S		

**Key to chemical resistance:**    **R = resistant**    **S = suitable**    **U = unsuitable**

#### Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energizers (preload elements). General application in petroleum fluids, water, greases, mineral oils, oil and gas industry.

#### Analysis and Evaluation

The mentioned properties are only valid for test pieces of the corresponding ISO, DIN and ASTM standards. They cannot be directly related to seals, gaskets and other sealing products and should be used only as a general guide.